FINAL REPORT

CERTIFICATE No.: 25780



ABN 62 008 528 523 Taylor Avenue New Berrima NSW 2577 Locked Bag 4 New Berrima NSW 2577 T +61 2 4860 2222

TEST CERTIFICATE OF:	Maldon Daily Despatch Builders Cement			
PRODUCED AT:	Boral Cement Limited Maldon			
TESTED AT:	Berrima Works Laboratory			
SAMPLE IDENTIFICATION:	MDDBU2400719			
DATE DESPATCHED:	2/26/2024			

PROPERTY	REQUIREM	REQUIREMENTS OF AS 3972						
Compressive Strength (AS/NZS 2350.11)								
3 Day			20.0 MPa					
7 Day	Minimum	20 MPa	31.3 MPa					
28 Day	Minimum	35 MPa	50.9 MPa					
Setting Time (AS/NZS 2350.4)								
Initial	Minimum	45 mins	180 mins					
Final	Maximum	600 mins	240 mins					
Soundness (AS/NZS 2350.5)	Maximum	5 mm	1 mm					
SO ₃ (TM 10.01.07)	Maximum	3.5 %	2.1 %					
CI (AS 2350.2)	Maximum	0.10 %	0.01 %					

OTHER REPORTABLE PROPERTIES	
CHEMICAL	

EMICAL	PHYSICAL			
	Normal Consistency	(AS/NZS 2350.3)	28.2 %	
	Fineness Index	(AS/NZS 2350.8)	350 m ² /kg	

REMARKS

Preparation of mortar and moulding of specimens in accordance with AS 2350.12.

Sampling not carried out by laboratory. Samples tested as received and results only relate to the item tested. This cement is a Type GB cement with nominally 35% slag.

W

Accredited for compliance with ISO/IEC 17025 - Testing

Marc Smith Technical Services Manager Date of Issue: 4/24/2024